Hardness and Roughness by AFM-HR Analysis of Nano-Hydroxyapatite

Dora E. Ledesma-Carrión

Dirección de Investigación, Instituto Nacional de Estadística y Geografía, Cd. de México, Cd. Mx., 03730 México

Abstract: Stoichiometric nano-hydroxyapatite is synthesized and compacted by UP (Uniaxial pressing) and CIP (Cold isostatic pressing). It is sintered (S) and subsequently is immersed in SBF (Synthetic body fluid). Hardness and roughness are analyzed in each part of process. The relationship between hardness and roughness is proportional after UP. While in the CIP and sintering the relationship is symmetric with a maximum. After immersion there is no clear functional relationship. Roughness changes at each stage of the process are -13.3% (UP → CIP), 22.10% (CIP → S) and -61.5% (S → SBF), respectively. Analogously, for area particle: 405.60%, 120.20% and -99.8%.

Key words: Hardness, roughness, atomic force microscopy, hydroxyapatite, compaction.

PACS: 01.30.-y, 01.30.Xx, 01.30.Tt.

1. Introduction

Hydroxyapatite is main bone substitute and its mechanical properties depend of grain size, porosity, density, hardness and toughness.

Atomic force microscopy and nano-indentation are surface analysis techniques, it is possible to measure a roughness and hardness of a sample surface at a high resolution, to distinguish a sample based on its mechanical properties, tests can be performed at variable displacements so that properties can be determined as a function changing substrate effect.

R. Roop Kumar and M. Wang [1] reported hardness, particle size and density of different samples of hydroxyapatite composites by nano-indentation and Fritsch particle size analyser, inter alia: HA- α TCP (2.56, 3.128, 1.5364; [GPa, μ m, g/cm³]), Spherical HA (6.76, 24,548, 2.9534), in-house-HA (6.19, 16,338, 2.9534) and P81B (0.338, 7,460, 1.5657). The last one and spherical HA are commercial material and the other were by wet method [1]. Nano-rods-HA synthesized via the wet precipitation process of ~ 50

$\times 15$ nm² and surface area of 120 m²/g by Wang and Shaw [2]. These have also been characterized by nano-indentation and BET method. Hardness follows the Hall-Petch relationship, ~ 5.3 GPa Knoop hardness, and particle size of 67nm with heat treatment at 850 °C for densification. For the HAcc with 100-200 nm of diameter the Knoop hardness is 4.58-5.0 GPa. The Table 1 summarizes this information.

2. Materials and Methods

2.1 Synthesis

Hydroxyapatite was synthesized by co-precipitation method. A rod-like morphology with particle size of 20-50 nm $\times$ 100-200 nm, particle average size of 175.9 nm with 1-modal, pore radii of 1.22 nm and stoichiometric and anisotropic hydroxyapatite was prepared by reacting calcium hydroxide and a phosphoric acid solution. Hydroxyapatite powder [3] was treated with heat at 680 °C during 3 h in Ar atmosphere (HAcc).

2.2 Compaction

HAcc was submitted to cold uniaxial and isostatic compaction. The UP was a Daniels of Stroud Stryd glos

Corresponding author: Dora E. Ledesma-Carrión, PhD.
Research fields: Biomaterials, optimization and mathematical models.

Table 1 Density, diameter, roughness and hardness for different hydroxyapatites.

Sample	Density [g/cm ³]	Diameter [nm]	Roughness [nm]	Hardness Hc [GPa]
HAcc UP	1.7535	1,093	200.10	0.170
HAcc CIP	1.9301	2,028	247.25	0.518
HAcc S	2.0368	1,233	229.58	0.322
HAcc SBF	1.8367	74	90.39	3.208
SHA*	2.9534	24,548		6.76
In-house HA*	2.8125	16,338		6.19
aTCP*	1.5364	3,128		2.56
P81B*	1.5657	7,460		0.338
P120*	2.7989	3,290		0.237
P88*	2.8125	4,530		0.158

*R. Roop Kumer, M. Wang.

No. 714987 RAM DIA 6". These tablets are named "green pieces". 5 g HAcc powder were compacted under 30 Kg/cm² during 90 s. Dies diameter were 1.00-1.25 cm of steel 316L. CIP was made with a Yuken Model 334 press applied 400 MPa during one cycle of four steps: Step 1: 0-100MPa; step 2: 101-200 MPa; step 3: 201-300 MPa; step 4: 301-400 MPa. Time of step is 30 s [4].

2.3 Sinter

According to literature [5-7], there is nucleation from 600 °C, but the best occurs at 1,350 °C for 7 h. HAcc was sintered at 925 °C in a process of one ramp: from 25 to 925 °C at a rate of 10 °C/min, the carrier gas Ar is incorporated from 580 °C. And at 925 °C it is maintained for 2 h. After it allowed to cool at rate of 10 °C/min up to get 25 °C temperature. Ar turns off when it reaches 580 °C. They will not be removed from the furnace until two days later to avoid thermal shock. Sintering was made in a 6000 Thermolyne (0 – 999 °C). Each tablet face was scanned into 50 × 50 µm² areas for 5 zones and 1,250 scans/s. AFM-HR is a diMultiMode V - AFM Veeco, Nanoscope V controller, tapping mode, 50 × 50 µm² areas and 1,250 scans/s. Silicon tip. Adjusted force of 50 µN.

2.4 Bioactivity

The grid is set to 70 °C to keep the liquid at 36.5 °C: PH = 7.25 with 50 mM trihydroxy

methyl-aminomethane and 45 mM of hydrochloric acid. Ion concentrations and compounds for SBF used Kukobo et al. modified process [8].

Tablets enclosed inside assay tubes with 40 mL SBF were place into container. The tubes were immersed into thermic bath with ionized water at 37 °C. As tablets were drawn from the solution they were washed twice in deionized water and dried at room temperature for 2 days. When the tablets were taken out of SBF, liquid pH was measured and when dried them were weighed to record the change of pH and mass.

3. Results and Discussion

AFM analysis for pores and particles was applied on the tablets under UP, CIP, and later sintering. Finally, immersion into SBF during 1 day.

The analysis was applying the software indentation 4.16 and gwyddeen version 2.41. Track each tablet under each process was made. The results appear in Figs. 1 and 2 and Tables 1-3. Note: Hardness or roughness measures are not possible on all zones of samples, 10 zones for each sample.

The topographies of one tablet into each process step are showed in Fig. 1: (a) regular distribution in the UP, (b) rearrangement during the CIP, It is observed grooves and tetragonal symmetry of HAcc, (c) alignment of grooves after the sintering and (d) After immersing the tablets in SBF one day there is

Fig. 1 AFM-HR, 3D images. Hydroxyapatite (HAcc) with (a) Uniaxial compaction (UP), (b) Isostatic compaction (CIP), (c) Sintering (S) and (d) Simulated body fluid (SBF) for 1 day.

Table 2 Summary of the analysis of particles for some zones samples of HAcc. roughness.

Sample code	Average roughness	Standar deviation (s.d.)	Diameter [nm]				Area [nm ²]			
Particle	[nm]	[nm]	Minimum	Maximun	Average	s.d.	Minimum	Maximun	Average	s.d.
HA U 1	242.2	377.0	895.5	6,761.20	2,006.30	1,599.10	629,881.60	35,273,368.00	5,064,248.00	8,263,780.50
HA U 2	151.3	225.2	895.5	7,275.40	1,469.60	1,188.80	629,881.60	41,572,184.00	2,784,076.50	6,510,063.00
HA U 3	182.8	399.5	895.5	6,761.20	1,500.40	1,151.50	629,881.60	35,903,252.00	2,778,889.30	6,224,157.50
HA I 1	303.2	541.9	895.5	15,091.90	3,167.90	3,670.50	629,881.60	178,256,480.00	16,679,264.00	39,503,888.00
HA I 2	233.0	418.0	895.5	15,588.60	5,527.10	6,397.80	629,881.60	190,854,112.00	51,965,228.00	83,790,824.00
HA I 3	67.1	103.0	895.5	2,831.90	1,261.20	590.40	629,881.60	6,298,816.00	1,502,025.30	1,616,937.30
HA I 4	63.3	94.5	895.5	3,102.20	1,266.80	545.10	629,881.60	7,558,579.00	1,490,424.00	1,476,203.10
HA S 1	285.6	462.0	895.5	15,144.90	2,703.10	3,368.80	629,881.60	179,516,256.00	14,361,300.00	40,729,932.00
HA S 2	83.1	124.8	895.5	6,139.50	1,974.80	1,776.00	629,881.60	29,604,434.00	5,374,989.50	9,077,624.00
HA S 3	335.1	444.7	895.5	9,306.70	1,598.60	1,468.80	629,881.60	68,027,208.00	3,662,102.30	10,735,525.00

U-uniaxial compression, I-isostatic compression and S-sinterized.

Sample code	Average roughness	Standar deviation (s.d.)	Diameter [nm]				Area [nm ²]			
Particle	[nm]	[nm]	Minimum	Maximun	Average	s.d.	Minimum	Maximun	Average	s.d.
HA-1 SBF	53.925	80.348	44.424	421.447	81.179	68.725	1,550.003	139,500.281	8,862.595	18,943.316
HA-2 SBF	112.040	210.635	44.424	453.042	83.985	81.313	1,550.003	145,700.297	10,141.449	25,163.076
HA-3 SBF	227.380	432.022	44.424	446.459	68.103	48.033	1,550.003	150,350.297	5,397.133	13,764.532
HA-5 SBF	37.073	66.361	44.424	423.782	61.709	49.070	1,550.003	141,050.281	4,856.676	16,418.199

SBF-Simuated body fluid.

Table 3 Comparison per process: uniaxial compaction, isostatic compaction, sintering and simulated body fluid.

Sample particle	Average roughness [nm]	Difference by process Process $U \rightarrow I \rightarrow S$	Sample particle	Average roughness [nm]	Difference by process Process $U \rightarrow I \rightarrow S \rightarrow SBF$
HA U	192.139		HA SBF	90.39	-54.8%
HA I	166.674	-13.3%			Process $S \rightarrow SBF$
HA S	234.615	22.1%			-61.5%
Sample particle	Average diameter [nm]	Difference by process	Sample particle	Average diameter [nm]	Difference by process
HA U	1658.790	process $U \rightarrow I \rightarrow S$	HA SBF	73.7	Process $U \rightarrow I \rightarrow S \rightarrow SBF$
HA I	2805.744	69.1%			-95.6%
HA S	2092.178	26.1%			Process $S \rightarrow SBF$
					-96.5%
Sample particle	Average area [nm ²]	Difference by process	Sample particle	Average area [nm ²]	Difference by process
HA U	3,542,404.58	process $U \rightarrow I \rightarrow S$	HA SBF	7,314.50	Process $U \rightarrow I \rightarrow S \rightarrow SBF$
HA I	17,909,235	405.6%			-99.8%
HA S	7,799,464	120.2%			Process $S \rightarrow SBF$
					-99.9%

HA-hydroxyapatite HAcc; U-uniaxial compaction; I-cold isostatic compaction; S-sintering; SBF-Simulated body fluid.

Fig. 2 Maximal hardness versus roughness in each track of process. (a) uniaxial compaction (UP), (b) isostatic compaction (CIP), (c) sintering (S) and (d) simulated body fluid (SBF) 1 day, (e) roughness, hardness vs diameter in each step of process and, (f) roughness, hardness vs density in each step of process.

evidence of the diffusion process, face appears smoothed with rounded structures.

From Table 1, HAcc SBF has similar mechanical properties that α -TCP (Hc) and HA-Wang-Shaw (Knoop hardness), and HAcc S with P81B (density). From Tables 2 and 3, the increase is observed in the size of particle after CIP 69.1% with regard to the “green” tablet (after UP). During sinter it is reduced up to 25.43%. Drastic particle size reduction occurs in the SBF. The total effect is a decreasing of 95.6%. The same behavior is shown for particle area. During the UP the particles agglutinate increasing the spaces inter-grains. Later, during the CIP the particles re-get accommodated increasing the size of grain. Finally, after sinter them, the particles return to agglutinate again. Tablets gain in nano-hardness (and elasticity [4]).

The liquid pH where tablets were immersed during one day is 8 (initial pH = 7.25) with a 41.2% loss weight.

4. Conclusions

There is a direct relationship between hardness and roughness after UP from 10,703 Kg/mm² with a slope of 1.6. After CIP both maximum hardness and roughness are reached in the central part of the tablet. Subsequently, sintering, the maximum hardness is reduced 38.7% and the roughness increased by 3.69%. Finally, there is no direct relationship between

hardness and roughness after immersion in synthetic body fluid. This is evidence of the presence of chemical reactions.

References

- [1] Kumar, R. R. and Wang, M. 2002. “Modulus and Hardness Evaluations of Sintered Bioceramic Powders and Functionally Graded Bioactive Composite by Nano-Indentation.” *Materials Science and Engineering A* 338: 230-6.
- [2] Wang, J. and Shaw, L. 2009. “Nanocrystalline Hydroxyapatite with Simultaneous Enhancements in Hardness and Toughness.” *Biomaterials* 30: 6565-72.
- [3] Ledesma-Carrión, D. E. 2015. “Modification on the Synthesis Process of Hydroxyapatite, Asian Journal of Science and Technology.” 6 (4): 1311-5.
- [4] Ledesma-Carrión, D. E. 2015. “Nano-Hardness and Elasticity for Hydroxyapatite Before and After of Immersing it into Simulated Body Fluid.” *International Journal of Emerging Trends in Science and Technology* 2 (6): 2704-9.
- [5] Ohgaki, M., Nakamura, S., Okura, T. and Yamashita, K. 2000. “Enhanced Mineralization on Electrically Polarized Hydroxyapatite Ceramics in Culture Medium.” *J. Ceram. Soc. Japan* 11 (108):1037-40.
- [6] Chun-Hway, H. 1991. “Some Considerations of Determination of Residual Stresses and Young’s Moduli in Ceramic Coatings.” *J. Am. Ceram. Soc.* 74:1646-9.
- [7] Afshar, A., Ghorbani, M., Ehsani, N., Saeri, M. R. and Sorrel, C. C. 2003. “Some Important Factors in Wet Precipitation Process of Hydroxyapatite.” *Materials & Design, Num.* 24: 197-202.
- [8] Oyane, A., Kim, H. -M., Furuya, T., Kokubo, T., Miyazaki, T. and Nakamura, T. 2003. “Preparation and Assessment of Revised Simulated Body Fluids.” *Journal of Biomedical Materials Research* 65 A: 188-95.